

PRODUITS DECOUPABLES

PRODUITS IMPRIMABLES

		PRODUITS DECOUPABLES															PRODUITS IMPRIMABLES																								
TRANSFER CONDITIONS	Température (°C)	160	160	150	160	130	Standard 160 150 130	Nylon* 150	160	160	160	160	150	160	160	160	160	160	160	160	160	160	Standard 160 150 130	Nylon* 150	160	160	160	160	150	135	160	160	160	160	160	160	160	160	160		
	Pression (bar)	2,5 3,0	2,5 3,0	2,0	2,5 3,0	2,5 3,0	2,5 3,0	2,0	2,0	2,0	2,0	2,5 3,0	2	3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0	2,5 3,0				
	Temps (sec.)	15	15	Pre-pressing 4 Second pressing 10	15	10	3 4 5	5 5 10*	15	15	15	15	Pre-pressing 4 Second pressing 10	25	15	15	15	15	15	15	15	15	15	3 4 5	5 5 10*	15	15	15	15	15	Pre-pressing 4 Second pressing 10	15	15	15	15	15	15	15	15	15	15
	Echeniller (W = Chaud / C = Froid)	W	W	W	W	W	W & C	W & C	W	C	W	W	W	C	C	C	C	W	W	W	C	W	W	W	W	W	W	C	W	C	W	W	C	C	W	W	W	W			
WASH CONDITIONS	Résistance au lavage (°C)	80	60	40	80	40	60	40	60	40	40	60	40	60	40	Hand-wash only	60	60	60	60	40	60	60	40	80	60	40	40	40	40	40	40	40	60	60	60	40	90	60	40	
	Sèche-linge	●			●	●	●**		●	●		●		●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	
	Nettoyage à sec	●	●		●	●	●											●																							

*POLI-FLEX® TURBO & TURBO PRINT
 • Pre-pressing 5 sec.
 • Pressing on Nylon 5 sec.
 • After Removing PET Liner 10 sec.

**POLI-FLEX® TURBO PRINT
 commercial tumble dryer up to 100°C