

MADEIRA

Technical Datasheet

09.09.2019

BURMILANA No.12

Article Description Wool Effect Embroidery Thread

Composition 50% wool / 50% acrylic

Count 330 dtex x 2 / 300 den x 2

Make Up Available 1000m cone

Recommended needle size 100/16

Fastness Rating – Scale 1 (worst) – 5 (best)

Fastness to washing at 50°C DIN EN ISO 105-C01/M & S C4A 4-5

Fastness to water (damp for 4hrs at 37°C) DIN EN ISO 105_E01/M & S C6 4-5

Fastness to rubbing dry (10 rubs on dry white Fabric) DIN EN ISO 105-X12/M & S C8 4

Fastness to rubbing wet (10 rubs on wet white Fabric) DIN EN ISO 105-X12/M & S C8 3-4

Fastness Rating – Scale 1 (worst) – 8 (best)

Fastness to light (100hrs xenon light) DIN EN ISO 105-B02 ≥5

Due to different dye stuffs not applicable to all colors.

Mechanical – Technological Values

Tensile Strength cN (force until thread breaks, in Centinewton) DIN EN ISO 2062 ca. 860cN

Elongation (% of stretch extension with weight tension until breaks) ca.18%

Recommendations for care



Color Card No.

69

Oeko-Tex



To improve this product Madeira reserves the right to alter the specifications or modify the appearance of products without notice. Information and technical data in this document are guidelines and no warranted characteristics. Small variations due to production process are possible.

MADEIRA Garnfabrik
Rudolf Schmidt KG

Zinkmattenstraße 38
D-79108 Freiburg

Tel.: +49 (0) 761 – 51 04 00
E-Mail: service@madeira.de

MADEIRA