

BURMILANA CO

Article Description Wool Effect Embroidery Thread

Composition 50% cotton / 50% acrylic

Count 330 dtex x 2 / 300 den x 2

Make Up Available 1000m cone

Recommended needle size 100/16

Fastness Rating – Scale 1 (worst) – 5 (best)

Fastness to washing at 50°C	DIN EN ISO 105-C02/M & S C4A	4-5
Fastness to water	DIN 54005 M & S C6	4-5
Fastness to rubbing dry (10 rubs on dry white Fabric)	DIN EN ISO 105-X12/M & S C8	4
Fastness to rubbing wet (10 rubs on wet white Fabric)	DIN EN ISO 105-X12/M & S C8	3-4
Determination of the colourfastness of articles for common use – Part 1: Test with artificial saliva DIN 53160-1		4-5
Determination of the colourfastness of articles for common use – Part 2: Test with artificial sweat DIN 53160-2		4-5

Fastness Rating – Scale 1 (worst) – 8 (best)

Fastness to light (100hrs xenon light) DIN EN ISO 105-B02 ≥5

Due to different dye stuffs not applicable to all colors.

Mechanical – Technological Values

Tensile Strength cN (force until thread breaks, in Centinewton) DIN EN ISO 2062 ca.800cN

Elongation (% of stretch extension with weight tension until breaks) ca.8%

Recommendations for care



Color Card No.

69

Oeko-Tex



To improve this product Madeira reserves the right to alter the specifications or modify the appearance of products without notice. Information and technical data in this document are guidelines and no warranted characteristics. Small variations due to production process are possible.