MADEIRA Technical Datasheet

05.05.2021

Polyneon Green No. 40

Article Description	Machine Embroidery Thread
Composition	100% polyester [filament; recycled]
Count	135 dtex x 2 / 120 den x 2
Make Up Available	5000 m cone
Recommended needle size	60/8 – 75/11

Fastness Rating – Scale 1 (worst) – 5 (best)			
Fastness to washing at 95°C	DIN EN ISO 105-C04/M & S C4A	4-5	
Fastness to water (damp for 4hrs at 37°C)	DIN EN ISO 105-E01/M & S C6	4-5	
Fastness to rubbing dry (10 rubs on dry white fabric)	DIN EN ISO 105-X12/M & S C8	4	
Fastness to rubbing wet (10 rubs on wet white fabric)	DIN EN ISO 105-X12/M & S C8	3-4	
Fastness to dry cleaning	DIN EN ISO 105-D01	4-5	
Fastness to bleaching with hypochlorite	DIN EN ISO 105-N01	4-5	
Determination of the colourfastness of articles for common use -	Part 1: Test with artificial saliva DIN 53160-1	4-5	
Determination of the colourfastness of articles for common use -	Part 2: Test with artificial sweat DIN 53160-2	4-5	
Factness Dating - Scale 1 (worst) - 9 (host)			

Fastness Rating – Scale 1 (worst) – 8 (best)

Fastness to light (100hrs xenon light)

DIN EN ISO 105-B02

5

Due to the used dye chemicals, this rating cannot be achieved for all colors.

Mechanical - Technological Values

Tensile Strength cN (force until thread breaks, in Centinewton DIN EN ISO 2062 ca. 1250 Elongation (% of stretch extension with weight tension until breaks) ca. 28% Shrinkage (shrinkage at boiling water) DIN 53866 T2 < 1%

Recommendations for care



 \triangle max. 20g/l active chlorine- max. 30°C - max. 30 min

Certification



To improve this product Madeira reserves the right to alter the specifications or modify the appearance of products without notice. Information and technical data in this document are guidelines and no warranted characteristics. Small variations due to production process are possible.

MADEIRA Garnfabrik Rudolf Schmidt KG Zinkmattenstraße 38 D-79108 Freiburg Tel.: +49 (0) 761 – 51 04 00 E-Mail: service@madeira.de

